



One Industrial Dr. ~ P.O. Box 130 ~ Constantine, MI 49042
Phone: 269.279.1700 ~ Fax: 269.435.7760

PRODUCT DATA SHEET

DATE:	11/23/2011
PRODUCT:	.100 Valdor #2 Board

Environmental Conditioning: Temperature 70°F ± 2°F, Humidity 50% ± 5%

NOTE: Extreme environmental condition changes will cause paperboard characteristics to change.
Fibre Converters, Inc. is not responsible for these changes or the resulting effects on the product.

CHARACTERISTIC	SPECIFICATION
Caliper (thickness)	.100" ±0.005"
Basis Weight	350 Lb/MSF Min.
Moisture Content	4 - 8%
Mullen Burst	400 Min.
Z Directional Test (ZDT)	45 psi Min.

A handwritten signature in black ink, appearing to read "C. Brown", is written over a horizontal line.

Quality Department